

**DESCRIPTION**

Total thickness	En ISO 24346	mm	2.50
Thickness of the wearlayer	EN ISO 24340	mm	0.55
Weight	EN ISO 23997	g/m <sup>2</sup>	4100
Plank size	EN ISO 24342	cm	45.7 x 91.4 / 61 x 61 / 18.4 x 121.9 15.2 x 91.4 / 45.7 x 45.7 / 10.2 x 91.4

**CLASSIFICATION**

Norm product specification	-	-	ISO 19322
Fire rating	IMO Resolution		MSC 307(88) Part 5 MSC 307(88) Part 2
	Maritime Approvals		Marine Equipment Directive US Coast Guard Transport Canada SOLAS 74
Static electrical propensity	EN 1815	kV	< 2

**PERFORMANCE**

Wet slip resistance	DIN 51130	class	R10*
Castor chair test	ISO 4918	-	OK
Dimensional stability (norm)	EN ISO 23999	%	≤ 0.25
Dimensional stability (average measured value)	EN ISO 23999	%	≤ 0.15
Residual indentation	EN ISO 24343-1	mm	≤ 0.10
Thermal conductivity	EN ISO 10456	W/(m.K)	0.25
Colour fastness	EN 20 105 – B02	degree	≥ 6
Chemical resistance	EN ISO 26987	-	OK
Surface treatment	-	-	PUR
TVOC after 28 days	ISO 16000-6	µg/m <sup>3</sup>	< 10

\*All designs are R10 according to DIN 51130 except Design Chevron (R9)

