

DESCRIPTION

| | | | |
|-----------------------|-----------------------|-------------------|--------|
| Total thickness | EN ISO 24346 (EN 428) | mm | 2 |
| Weight | EN ISO 23997 (EN430) | kg/m ² | 3.40 |
| Width length of sheet | EN ISO 24341 (EN426) | cm/lm | 200/20 |

CLASSIFICATION

| | | | |
|------------------------------|--------------------|----|--|
| Norm product specification | - | - | EN ISO 10581 (EN 649) |
| | IMO Resolution | | MSC 61 (67) Part 5 MSC 61 (67) Part 2 |
| | Maritime Approvals | | Marine Equipment Directive US Coast Guard Transport Canada SOLAS 74 |
| Static electrical propensity | EN 1815 | kV | < 2 |

PERFORMANCE

| | | | |
|-------------------------|-----------------------------|-------------------|-----------|
| Wet slip resistance | DIN 51130 | class | R9 |
| Wear resistance | EN 660.2 | mm ³ | ≤ 7.5 |
| Wear group | EN 649 | group | M |
| Type binder content | ISO 10581 | Type | II |
| Dimensional stability | EN ISO 2399 (EN434) | % | ≤ 0.40 |
| Residual indentation | EN ISO 24343-1 (EN433) | mm | ≈ 0.03 |
| Thermal conductivity | EN ISO 10456 (EN 12 524) | W/(m.K) | 0.25 |
| Colour fastness | EN 20 105 – B02 | degree | ≥ 6 |
| Resistance to chemicals | EN ISO 26987 (EN423) | - | OK |
| Surface Treatment | - | - | PUR |
| TVOC after 28 days | ISO 16000-6 | µg/m ³ | < 10 |

